

CLAIMS

1. An internal member for a plasma treating vessel comprising a substrate and a Y_2O_3 sprayed coating covered on a surface thereof.
2. An internal member for a plasma treating vessel comprising a substrate, a metal coating formed on a surface thereof as an undercoat, and a Y_2O_3 sprayed coating formed on the undercoat as a top coat.
3. An internal member for a plasma treating vessel comprising a substrate, a metal film formed on a surface thereof as an undercoat, a middle layer formed on the undercoat and a Y_2O_3 sprayed coating formed on the middle layer as a top coat.
4. An internal member for a plasma treating vessel according to claim 1, 2 or 3, wherein the metal coating as the undercoat is a coating of one or more metals or alloys selected from Ni and an alloy thereof, W and an alloy thereof, Mo and an alloy thereof and Ti and an alloy thereof and having a thickness of 50-500 μm .
5. An internal member for a plasma treating vessel according to claim 1, 2 or 3, wherein the middle layer is a layer of Al_2O_3 , or a mixture of Al_2O_3 and Y_2O_3 .
6. An internal member for a plasma treating vessel according to claim 5, wherein the middle layer is formed by a layer having a gradient concentration such that a concentration of Al_2O_3 is high at a side of the undercoat and a concentration of Y_2O_3 is high at a side of the top coat.
7. An internal member for a plasma treating vessel according to claim 1, 2 or 3, wherein the Y_2O_3 sprayed coating is a coating having a porosity of 0.5-10% and a thickness of 50-2000 μm .
8. A method of producing an internal member for a plasma treating vessel, which comprises covering Y_2O_3 on a surface of a substrate through a spraying process to form a Y_2O_3 sprayed coating.

9. A method of producing an internal member for a plasma treating vessel, which comprises applying at least one surface treating process selected from CVD process, PVD process and thermal spraying process to a surface of a substrate to form a composite layer consisting of a layer of a metal of Ni, W, Mo or Ti or an alloy thereof as an undercoat and Y_2O_3 as a top coat.

10. A method of producing an internal member for a plasma treating vessel, which comprises applying at least one surface treating process selected from CVD process, PVD process and thermal spraying process to a surface of a substrate to form a composite layer consisting of a layer of a metal of Ni, W, Mo or Ti or an alloy thereof as an undercoat, Al_2O_3 or a mixture of Al_2O_3 and Y_2O_3 as a middle layer and Y_2O_3 as a top coat.